

# STUCCO TERRA



Apply one coat of PRIMER MULTI-USE rolled, brushed or sprayed. Let dry 6 hours.



Apply first coat of tinted STUCCO TERRA with a roller (with a medium – heavy nap) to form peaks creating lots of texture.



Option A (one step process): when product is just set ( before “in love” ), knock down the peaks with a stainless steel trowel working the same area in the same direction, then going to other areas in a different direction, to obtain stone effects.



Option B (2 step process): after 48 hours, use the same roller and STUCCO TERRA (or different lighter color or shade), roll and skim right away (using both hands) in order to duplicate and accentuate the texture created in the first step.



Both Options A & B: while product is still “in love” burnish with stainless steel trowel .



Both Options A & B: after 24 hours apply 1 coat of NEUTRAL or PEARLESCENT WAX with trowel, cheesecloth (always using small strokes from wet to dry) or a rag (circular motions).



Both Options A & B: when wax is dry after 2 hours, polish with “wooly” or plastic bag.